

# TECAFORM AH SD natural - Stock Shapes

## Chemical Designation

POM-C (Polyacetal (Copolymer))

## Colour

ivory opaque

## Density

1.35 g/cm<sup>3</sup>

## Fillers

antistatic agent

## Main features

- antistatic
- soot-free
- high strength
- good wear properties
- good chemical resistance
- high stiffness
- difficult to bond
- high toughness

## Target Industries

- semiconductor technology
- chemical technology
- electronics
- food technology
- mechanical engineering

## Mechanical properties

<b>Mechanical properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Modulus of elasticity (tensile test)	1mm/min	1300	MPa	DIN EN ISO 527-2	1)
Tensile strength	50mm/min	39	MPa	DIN EN ISO 527-2	
Tensile strength at yield	50mm/min	39	MPa	DIN EN ISO 527-2	
Elongation at yield	50mm/min	23	%	DIN EN ISO 527-2	
Elongation at break	50mm/min	23	%	DIN EN ISO 527-2	
Flexural strength	2mm/min, 10 N	46	MPa	DIN EN ISO 178	2)
Modulus of elasticity (flexural test)	2mm/min, 10 N	1200	MPa	DIN EN ISO 178	
Compression strength	1% / 2% 5mm/min, 10 N	12 / 19	MPa	EN ISO 604	3)
Compression modulus	5mm/min, 10 N	1100	MPa	EN ISO 604	4)
Impact strength (Charpy)	max. 7,5J	n.b.	kJ/m <sup>2</sup>	DIN EN ISO 179-1eU	5)
Notched impact strength (Charpy)	max. 7,5J	9	kJ/m <sup>2</sup>	DIN EN ISO 179-1eA	
Ball indentation hardness		74	MPa	ISO 2039-1	6)

## Thermal properties

<b>Thermal properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Glass transition temperature		-60	°C	DIN 53765	1)
Melting temperature		165	°C	DIN 53765	
Service temperature	short term	140	°C		2)
Service temperature	long term	100	°C		
Thermal expansion (CLTE)	23-60°C, long.	16	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	23-100°C, long.	17	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Specific heat		1.6	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity		0.30	W/(K*m)	ISO 22007-4:2008	

## Electrical properties

<b>Electrical properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Specific surface resistance	Silver electrode, 23°C, 50% r.h.	10 <sup>9</sup> - 10 <sup>11</sup>	Ω	DIN IEC 60093	1)
Specific volume resistance	Silver electrode, 23°C, 50% r.h.	10 <sup>9</sup>	Ω*cm	DIN IEC 60093	(2) Specimen in 1mm thickness
Dielectric strength	23°C, 50% r.h.	5	kV/mm	ISO 60243-1	2)
Resistance to tracking (CTI)	Platin electrode, 23°C, 50% r.h., solvent A	600	V	DIN EN 60112	

## Other properties

<b>Other properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Water absorption	24h / 96h (23°C)	0.9 / 1.8	%	DIN EN ISO 62	1)
Resistance to hot water/ bases	(+)	-	-		2)
Resistance to weathering	-	-	-		3)
Flammability (UL94)	corresponding to	HB		DIN IEC 60695-11-10;	4)

- (1) Ø ca. 50mm, h=13mm
- (2) (+) limited resistance
- (3) - poor resistance
- (4) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensinger-online.com](http://www.ensinger-online.com). Technical changes reserved.