

TECASINT 2021 black - Stock Shapes

Chemical Designation

PI (Polyimide)

Colour

black

Density

1.45 g/cm³

Fillers

15% graphite

Main features

- very good slide and wear properties
- very good thermal stability
- high thermal and mechanical capacity
- good wear resistance
- resistance against high energy radiation
- high creep resistance
- good chemical resistance
- sensitive to hydrolysis in higher thermal range

Target Industries

- automotive industry
- aircraft and aerospace technology
- cryogenic engineering
- conveyor technology
- hot glass technology
- mechanical engineering
- precision engineering

Mechanical properties

| parameter | value | unit | norm | comment |
|---------------------------------------|----------------------------|-------------|-------------------|--------------------|
| Modulus of elasticity (tensile test) | 1 mm/min, 23°C | 4400 | MPa | DIN EN ISO 527-1 |
| Tensile strength | 50 mm/min, 23°C | 101 | MPa | DIN EN ISO 527-1 |
| Elongation at break | 50 mm/min, 23°C | 3.7 | % | DIN EN ISO 527-1 |
| Elongation at break | 10 mm/min, 23°C | 4.6 | % | DIN EN ISO 178 |
| Flexural strength | 10 mm/min, 23°C | 145 | MPa | DIN EN ISO 178 |
| Modulus of elasticity (flexural test) | 2 mm/min, 23°C | 4300 | MPa | DIN EN ISO 178 |
| Compression strength | 10 mm/min, 23°C | 300 | MPa | EN ISO 604 |
| Compression strength | 10mm/min, 10% strain, 23°C | 160 | MPa | EN ISO 604 |
| Compressive strain at break | 10 mm/min, 23°C | 43 | % | EN ISO 604 |
| Compression modulus | 1 mm/min, 23°C | 1900 | MPa | EN ISO 604 |
| Impact strength (Charpy) | max 7.5 J, 23°C | 36.7 | kJ/m ² | DIN EN ISO 179-1eU |
| Notched impact strength (Charpy) | max 7.5 J, 23°C | 2.9 | kJ/m ² | DIN EN ISO 179-1eA |
| Shore hardness | Shore D, 23°C | 87 | D | DIN 53505 |

Thermal properties

| parameter | value | unit | norm | comment |
|------------------------------|--------------|-------------|----------------------------------|----------------|
| Glass transition temperature | 370 | °C | - | 1) |
| Heat distortion temperature | 1.8 MPa | 335 | °C | DIN 53 461 |
| Service temperature | long-term | - | °C | - |
| Thermal expansion (CLTE) | 50-200°C | 3.8 / 4.5 | 10 ⁻⁵ K ⁻¹ | DIN 53 752 |
| Thermal expansion (CLTE) | 200-300°C | 4.6 / 5.4 | 10 ⁻⁵ K ⁻¹ | DIN 53 752 |

Other properties

| parameter | value | unit | norm | comment |
|---------------------|---------------------|-------------|-------------|-------------------------|
| Water absorption | 24 h in water, 23°C | 0.44 | % | DIN EN ISO 62 |
| Water absorption | 24 h in water, 80°C | 1.55 | % | DIN EN ISO 62 |
| Flammability (UL94) | corresponding to | V0 | | DIN IEC 60695-11-10; 1) |

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensinger-online.com. Technical changes reserved.